

Which lead-free bulk ceramics are suitable for electrical energy storage applications?

Here, we present an overview on the current state-of-the-art lead-free bulk ceramics for electrical energy storage applications, including SrTiO_3 , CaTiO_3 , BaTiO_3 , $(\text{Bi}_{0.5}\text{Na}_{0.5})\text{TiO}_3$, $(\text{K}_{0.5}\text{Na}_{0.5})\text{NbO}_3$, BiFeO_3 , AgNbO_3 and NaNbO_3 -based ceramics.

Why do we need lead-free ceramics?

Owing to the current global scenario of environmental pollution and the energy crisis, the development of new dielectrics using lead-free ceramics for application in advanced electronic and energy storage systems is essential because of the high power density and excellent stability of such ceramics.

Does lead-free bulk ceramics have ultrahigh energy storage density?

Significantly, the ultrahigh comprehensive performance ($W_{\text{rec}} \sim 10.06 \text{ J cm}^{-3}$ with $\eta \sim 90.8\%$) is realized in lead-free bulk ceramics, showing that the bottleneck of ultrahigh energy storage density ($W_{\text{rec}} \geq 10 \text{ J cm}^{-3}$) with ultrahigh efficiency ($\eta \geq 90\%$) simultaneously in lead-free bulk ceramics has been broken through.

Are lead-free anti-ferroelectric ceramics suitable for energy storage applications?

At present, the development of lead-free anti-ferroelectric ceramics for energy storage applications is focused on the AgNbO_3 (AN) and NaNbO_3 (NN) systems. The energy storage properties of AN and NN-based lead-free ceramics in representative previous reports are summarized in Table 6.

How stable is energy storage performance for lead-free ceramics?

Despite some attention has been paid to the thermal stability, cycling stability and frequency stability of energy storage performance for lead-free ceramics in recent years, the values of W_{rec} , cycle numbers and frequency are often less than 5 J cm^{-3} , 10^6 , and 1 kHz , respectively.

How can BT-based lead-free ceramics improve energy storage performance?

To better optimize the energy storage performance of BT-based lead-free ceramics, B. Liu et al. coated BT with Al_2O_3 and SiO_2 using the chemical coating method and reduced the average grain size below 200 nm . This led to improved breakdown strength (190 kV cm^{-1}) and enhanced energy storage density (0.725 J cm^{-3}). Q.

Both large maximum polarization and high applied electric field can be achieved in lead-free ceramics via layered structure optimization strategy, resulting in ultrahigh recoverable energy storage de...

The burgeoning significance of antiferroelectric (AFE) materials, particularly as viable candidates for electrostatic energy storage capacitors in power electronics, has sparked substantial interest. Among these, lead-free ...

The burgeoning significance of antiferroelectric (AFE) materials, particularly as viable candidates for electrostatic energy storage capacitors in power electronics, has sparked ...

Early dielectric capacitors (capacitors for short) are based on the dielectrics such as wax-impregnated paper and mica. Currently, commercially available solid-state capacitors ...

At present, the application of dielectric energy-storage ceramics is hindered by their low energy density and the fact that most of them contain elemental lead. Therefore, lead ...

Fig. 6 (e) illustrates the energy storage performance of BT, NN, KNN, BNT, and BFO-based lead-free energy storage ceramics reported in recent years (further information is ...

In this review, we present perspectives and challenges for lead-free energy-storage MLCCs. Initially, the energy-storage mechanism and device characterization are introduced; then, dielectric ceramics for energy ...

However, relatively low recoverable energy storage density (W_{rec}) or energy storage efficiency (η) of lead-free ceramic capacitors severely narrow their application areas ...